

To protect the privacy of customers or suppliers of Salamander Jewelry.
We erased their address from this document.

Purchasing Company		/		P.I./P.O.No.	/		Batch Number	HJ2018T1145		
Commodity			Material	Condition	Size & Specification	Quantity	Products Standard		Temperature	
Titanium Round Bar, Annealed Centerless Grinding			Gr23	M	Dia5mm x 2000-3000mm	480KGS	ASTM F136		20°C	
Titanium Round Bar, Annealed Centerless Grinding					Dia8mm x 2000-3000mm	620KGS	ASTM F136			
Chemical Composition (WT. %)										
TI Balance Ref. ASTM	Item	Fe	C	N	H	O	AL	V	Residuals	
	Size	0.25Max	0.08 Max.	0.05 Max.	0.012 Max.	0.13 Max.	5.5-6.50	3.5-4.5	Each (≤0.1)	Total (≤0.4)
	Dia5mm x 2000-3000mm	0.14	0.016	0.015	<0.001	0.07	6.1	3.9	≤0.1	≤0.4
Dia8mm x 2000-3000mm										
Mechanical Strength										
Inspection Item	Tensile Strength		0.2 Yield Strength		Elongation		Reduction of area		/	/
	(Rm/Mpa)		Rp0.2/Mpa		A(%)		Z(%) min.		/	/
Requirement	860		795		10 Min		25		/	/
Dia5mm x 2000-3000mm	1000		904		18		36			
Dia6mm x 2000-3000mm	950		900		20		33		/	/
Other Testing										
Testing Item	Dimensional Inspection		Surface Measurement		Micro Structure		Surface Contamination		Ultrasonic Test	
Result	ACCEPTABLE		ACCEPTABLE		ACCEPTABLE		ACCEPTABLE		/	

Hereby certify this product conforms to all specifically listed technical requirements, and other requirements for these specifications. Furthermore, we certify that the above stated quantitative results were derived from testing and analysis and are accordance with the reference specification requirements

To protect the privacy of customers or suppliers of Salamander Jewelry.
We erased their address from this document.